



**CANADA CENTRE FOR MINERAL AND ENERGY TECHNOLOGY  
(Former Mines Branch)**

---

ZINC PROMOTED Mo-Al HYDRODESULPHURIZATION CATALYSTS

M. TERNAN, R.J. WILLIAMS, and B.I. PARSONS

CANADIAN FOSSIL FUEL RESEARCH LABORATORY  
CATALYSIS RESEARCH SECTION

JULY 1975

---

FOR SUBMISSION TO JOURNAL OF CATALYSIS

NATIONAL ENERGY RESEARCH PROGRAM

ENERGY RESEARCH LABORATORIES  
REPORT ERP/ERL 75-91(J)

---

Crown Copyrights reserved

This document was produced  
by scanning the original publication.

Ce document est le produit d'une  
numérisation par balayage  
de la publication originale.

ZINC PROMOTED Mo-Al HYDRODESULPHURIZATION CATALYSTS

M. Ternan, R.J. Williams, and B.I. Parsons  
Energy Research Laboratories  
Department of Energy, Mines and Resources  
Ottawa, Ontario, K1A 0G1, Canada

Catalytic hydrodesulphurization processes are used in virtually every modern petroleum refinery. Other hydrotreating processes such as hydrocracking can be used to convert heavy oils and bitumens into synthetic crude oil. Recent work in our laboratory (1) is related to both areas of application. Commercial catalysts for hydrotreating and hydrorefining are usually Co-Mo or Ni-Mo on alumina. Some combinations of Ni-W are also used. Recently de Beer and co-workers (2,3) have evaluated Zn-Mo on alumina catalysts using thiophene at atmospheric pressure ( $1.013 \times 10^5 \text{ N/n}^2$ ). This note describes experiments which were performed to extend the evaluation of Zn-Mo on alumina catalysts to high pressures and to an industrial type feedstock. The heavy gas oil used in these studies was the 345-525°C portion of the product obtained by thermally hydrocracking Athabasca bitumen. Typical compounds in this gas oil contain from three to six condensed aromatic rings rather than the single ring thiophene used by de Beer and co-workers. Properties of the feedstock are listed in Table 1.

The catalysts were prepared by adding appropriate amounts of distilled water, trace quantities of nitric acid, and aqueous solutions of ammonium paramolybdate and of zinc nitrate to alpha alumina monohydrate powder (Continental Oil Company, 80 wt% Catapal N, 20 wt% Catapal SB) in a mix muller. A detailed description of the catalyst preparation procedure is available elsewhere (4). The powder was milled, dried at 120°C, calcined at 500°C and pressed into cylindrical pellets (L = D = 3.18 mm). The final form of the catalyst consisted of zinc and molybdenum oxides on  $\gamma$ -alumina. The catalyst pellets were evaluated in a bench-scale fixed bed reactor having a volume of 155 ml and a length to diameter ratio of 12. The reactor was filled sequentially from the bottom with 75 mm of berl saddles, 200 mm of catalyst pellets and 25 mm of berl saddles. The heavy gas oil, mixed with hydrogen (purity = 99.9 wt%) flowed continuously into the bottom of the reactor and up through the catalyst bed. The product leaving the top

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by "Xerox" or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY

of the reactor flowed to receiver vessels where the liquid and vapour were separated. Each experiment was performed at a pressure of  $1.39 \times 10^7 \text{ N/m}^2$  (2000 psig), a liquid volumetric space velocity of  $0.556 \text{ ks}^{-1}$  ( $2.0 \text{ hr}^{-1}$ ) based on the reactor volume occupied by the catalyst pellets, and a hydrogen flow rate of  $0.0718 \text{ l/s}$  at STP (5000 cf/bbl). When an experiment at one temperature was completed the reactor temperature was changed and the next experiment started using the same charge of catalyst. The reaction system was maintained at steady state conditions for 3.6 ks (1 hour) prior to, and for 7.2 ks (2 hours) during the period in which the sample of liquid product was collected. The amount of sulphur in the product sample was determined using an X-Ray fluorescence technique. A description of the experimental equipment and procedures used for catalyst evaluation has been given previously (1e).

Table 2 shows the results obtained during a typical series of experiments performed on a single charge of catalyst pellets. The purpose of the first experiment at  $400^\circ\text{C}$  was to stabilize and presulphide the catalyst. Gas oil and hydrogen contacted the catalyst for 25.2 ks (7 hours) prior to the beginning of the first  $420^\circ\text{C}$  experiment (No.2). The similarity of the results for both experiments at  $420^\circ\text{C}$  (No.2 and No.7) indicated that no appreciable change in catalyst activity occurred during the operating period. The catalyst was in the presence of hydrocarbon for 25.2 ks (7 hours) prior to experiment 2 and for 79.2 ks (22 hours) prior to experiment 7. This indicates that the initial 25.2 ks period was adequate to convert the oxide form of the catalyst into its sulphided working state.

The results in Figure 1 show how sulphur removal varied with the Zn/Mo ratio in the catalyst. Slight promotional and poisoning effects might be attributed to the catalysts which initially contained 12 wt% and 9 wt%  $\text{MoO}_3$  respectively. Whatever the trend it is clear that variations in zinc content only changed the weight percent sulphur removed from the gas oil by a few percent at the most. In contrast, previous work in our laboratory (4) using the same feedstock and processing conditions showed that the addition of cobalt to molybdenum on alumina catalysts increased the sulphur removed from the gas oil by an additional 33 wt%. This comparison indicates that the promotional effect of zinc is at least an order of magnitude smaller than cobalt.

These findings are in agreement with some of the results obtained

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by 'Xerox' or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY

1 by de Beer and co-workers (3) but contradict others (2). In the first paper by  
2 de Beer and co-workers (2) catalytic activity was shown to vary with metal/  
3 molybdenum ratio for cobalt, manganese, nickel and zinc. Although not stated  
4 explicitly it was implied that the measurements were made after the thiophene  
5 had contacted the catalyst for 6 ks (100 min.) and that this represented a  
6 steady state period. They found that at optimum metal/molybdenum ratios, all  
7 of the metals were good promoters, and that zinc was the best. DeBeer's data  
8 (2) have been given additional exposure by their presentation in two recent reviews  
9 of hydrodesulphurization (5,6). Our data (as shown in Figure 1) do not agree  
10 in any way with those presented by deBeer et al (2) in their first paper. In a  
11 second paper by deBeer and co-workers (3) an extensive decrease in activity of  
12 a zinc promoted catalyst (12 wt% Mo O<sub>3</sub>, Zn/Mo = 0.59) was reported as the time  
13 increased to 28.8 ks (8 hours). Furthermore the steady state activity of their  
14 zinc promoted catalyst was only slightly better than their equivalent unpromoted  
15 Mo on alumina catalyst. This second set of results tends to be consistent with  
16 our data in Figure 1. Therefore, we conclude that Zn-Mo catalysts are much less  
17 active for hydrodesulphurization than either Co-Mo or Ni-Mo on alumina catalysts.  
18  
19  
20  
21  
22  
23  
24

25 All of the above results can be explained by the conversion of the  
26 initial oxide form of the catalyst to its sulphided working state. The oxide  
27 form of the zinc promoted catalyst has a high activity for sulphur removal. After  
28 it has been converted to the sulphide form, its desulphurization activity diminishes  
29 considerably. Evidence for the above phenomenon is apparent in presently used  
30 technology. A zinc oxide desulphurization catalyst, not containing molybdenum,  
31 has been manufactured for over twenty years (7). In use the oxide is gradually  
32 converted to sulphide. When the catalyst has been fully sulphided, it must be  
33 replaced to maintain the desired degree of sulphur removal.  
34  
35  
36  
37

38 Completely sulphided catalysts appear to have been obtained in  
39 our high pressure experiments with a commercial type gas-oil and in the second  
40 study by deBeer and co-workers (3) at atmospheric pressure using thiophene. In  
41 both sets of experiments, comparable results were achieved after the catalyst  
42 had been in contact with hydrocarbon for periods of 25.2 ks (7 hours). The  
43 fact that these two sets of results agree constitutes strong evidence that  
44 thiophene is a good model compound for studying hydrodesulphurization of hydro-  
45 carbon mixtures. The inconsistency with the earlier results of deBeer and co-  
46 workers (2) was probably caused by their catalysts being only partially sulphided.  
47  
48

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by 'Xerox' or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY

The present work with zinc promoted Mo on alumina catalysts illustrates the need for hydrodesulphurization experiments to be performed with fully sulphided catalysts in their working states. Continuous flow experiments should be of sufficient duration to ensure that the catalyst has reached its steady-state condition. If a pulse method or other transient technique is to be used for catalyst evaluation, it is imperative that the catalyst be in its working state prior to the introduction of the transient.

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by "Xerox" or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY

1. E.C. McColgan, P.S. Soutar, and B.I. Parsons, "The Hydrocracking of Residual Oil and Tars", Mines Branch Research Reports (a) R-246, (b) R-253, (c) R-256, (d) R-261, (e) R-263, and (f) R-273, Department of Energy Mines and Resources, Ottawa (1971-74).
2. V.H.J. deBeer, T.H.M. van Sint Fiet, J.F. Engelen, A.C. van Haandel, M.W.J. Wolfs, C.H. Amberg, and G.C.A. Schuit, *J. Catalysis* 27, 357 (1972).
3. V.H.J. deBeer, T.H.M. van Sint Fiet, G.H.A.M. van der Steen, A.C. Zwaga, and G.C.A. Schuit, *J. Catalysis* 35, 297 (1974).
4. R.J. Williams, R.G. Draper, and B.I. Parsons, "Catalysts for Hydrocracking and Refining Heavy Oils and Tars, Part 1: The Effect of Cobalt to Molybdenum Ratio on Desulphurization and Denitrogenation". Mines Branch Technical Bulletin TB-187, Department of Energy Mines and Resources, Ottawa (1974).
5. G.C.A. Schuit and B.C. Gates, *AIChE J.* 19, 417 (1973).
6. C.H. Amberg, *J. Less Common Metals* 36, 339 (1974).
7. J.J. Phillipson, in "Catalyst Handbook" Springer-Verlag, New York, 1970, p. 49.

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by "Xerox" or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY

TABLE 1

PROPERTIES OF HEAVY GAS OIL

Boiling Range	345-525°C
Specific Gravity 60/60°F	0.992
Conradson Carbon Residue	0.97 wt%
Sulphur	3.59 wt%
Nitrogen	0.38 wt%
Vanadium	< 1 ppm

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by 'Xerox' or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY

TABLE 2

WT % S IN HYDRODESULPHURIZED PRODUCT  
(CATALYST = 9.0 WT% MoO<sub>3</sub> ON  $\gamma$ -ALUMINA)

Order in which Experiments Performed	Temperature °C	Sulphur Removed wt%
1	400	Presulphiding
2	420	65.7
3	400	48.8
4	380	35.9
5	435	76.9
6	450	86.9
7	420	64.9

This sheet is supplied for preparing master sheets for reproduction of paper or metal offset plates by "Xerox" or photography. All material to be reproduced (typed, drawn or mounted) is to be kept within the blue boundary lines.

SINCE THE ORIGINAL TYPED COPY IS TO BE PHOTOGRAPHED, PLEASE WRITE ANY PROPOSED REVISIONS ON THE CARBON COPY ONLY



Figure 1

Percent Sulphur Removal at 420°C versus  
Zinc to Molybdenum Ratio. The solid circles  
are for experiment 2 in each series. The open  
circles are for experiment 7 in each series.

